

X-TREME[®] SLM

Tex-Trude X-TREME Self Level Membrane (SLM) is a two component solvent free polymer-modified urethane asphalt. X-TREME SLM is designed to be installed around multiple penetrations (pipes) protruding through the X-TREME Vapor Barrier and slab. When used correctly, X-TREME SLM will form a consistent membrane around pipes and penetrations working with the X-TREME Vapor Barrier to form a monolithic system to protect the building against moisture intrusion.

X-TREME SLM is part of a complete line of best-of-class accessories that add to the extreme performance and ease of installation you receive with X-TREME Vapor Barrier - continuing to set the industry standards for durability, dependability and life-cycle superiority. Get the X-TREME advantage today for your business.

INSTALLATION ›

Prior to installation, perform a visual inspection of the X-TREME Vapor Barrier and the penetrations to insure a 6" overlap and all dust, dirt, debris, and moisture have been removed from the X-TREME Vapor Barrier to achieve maximum adhesion. It is important to apply the X-TREME SLM liberally, around all penetrations, and on top of the X-TREME Vapor Barrier at a minimum of 90 mils. Overlap the X-TREME SLM on the X-TREME Vapor Barrier 6" or more, to comply with the ASTM 1643. Be sure to pour a monolithic system were the X-TREME SLM has fully sealed around all penetrations and overlaps the X-TREME Vapor Barrier a minimum of 6" to secure proper coverage.



Warm conditions: Store out of direct sunlight. Perform normal installation, using industry knowledge of the guidelines for vapor barriers.

Cold conditions: In cold weather do not apply in temperatures below 40 degrees.

Follow all instructions on the labels on the X-TREME SLM containers.

Note: Only use X-TREME Accessory Products including X-TREME Tapes, X-TREME Mastic and X-TREME SLM to seal seams, edges, and penetrations.

TECHNICAL DATA >

X-TREME SLM		PACKAGING	
Thickness	90 mil	Pail	2 gallon pail unit
Permeance	0.01	Pails per pallet	36
Elongation	125%	Volume	1.24 Unit
Pot Life at 75 degrees	45 min	Coverage per sq ft	Approx. 16 sq ft
Initial Cure at 75 degrees	1 hour	Color	Black
Final Cure at 75 degrees	8 hours	Cold Weather Resistance	Excellent

LIMITED WARRANTY >

Tex-Trude warrants this product to meet the published specifications and to be free of defects in workmanship and materials at the time of shipment from our factory. If any X-TREME material proves to contain manufacture defects that substantially affect the performance, then Tex-Trude will at their option replace the material or refund the purchase price. This limited warranty is the only warranty offered by Tex-Trude, LP as it relates to X-TREME products. There are no other warranties, including the implied warranties of merchantability or fitness for a particular purpose. Tex-Trude specifically disclaims liability for any incidental, consequential, or other damages.